



Red Oak has a Janka Hardness rating of 1,220 lbf. It is a strong and heavy hardwood native to North America. The sapwood is a pale white to light brown color while the heartwood is a pinkish to reddish brown color. There is a coarse heavy texture that you can see and feel. Recommended stains include white/light colors, grays, browns, ebonized (black) and Muratti.



White Ash has a Janka Hardness rating of 1,320 lbf. It is a strong and heavy hardwood native to eastern North America. It is a naturally pale-colored hardwood. The sapwood is a white to light cream color while the heartwood is tan to light brown. It is a coarse heavy texture that you can see and feel. Recommended stains include stains in the white/light color, grays, browns, ebonized (black) and Muratti.




White Hard Maple has a Janka hardness rating of 1,450 lbf. It is a dense durable hardwood native to North America. The sapwood is nearly white to a cream color, while the heartwood tends to be a darker sometimes reddish hue brown. It has a very tight grain, giving off an almost glass like smooth texture. White Hard Maple is not a wood we offer stains for.




Hickory has a Janka hardness rating of 1,820 lbf. It typically comes from the eastern and midwestern United States, as well as parts of southern Canada and Mexico. It has a range of colors, including creamy white sapwood, golden tan brown and streaks of dark brown or reddish/pink hues. Recommended stains include white/light color, grays and browns.



Cherry has a Janka hardness rating of 950 lbf. It comes from the Eastern and Midwestern United States. It ranges from a rich red or a reddish brown and it known to darken over time. It has a nice buttery smooth texture. Recommended stains include stains in the red and brown family.



Makore, otherwise known as **African Cherry**, has a Janka hardness rating of 1,150 lbf. It comes from the rainforests of Western and Central Africa. The color ranges from pale pink to red/red-brown. The grain is straight but frequently features figure. It offers a buttery-smooth texture. The recommend stains include those in the red and brown family.




African Mahogany has a Janka hardness rating of 1,070 lbf. It comes from West and Central Africa. It is very similar to the popular Sapele Mahogany, but is lighter in color and weight. Color ranges from pale pink to a red brown. It is available in ribbon stripe and mix grain. It has a buttery smooth texture. Recommend stains include those in the red and brown family.



Sapele Mahogany has a Janka hardness rating of 1,410 lbf. It comes from the tropical rainforests between West, Central and East Africa. The color ranges from golden reddish brown to dark reddish brown with shimmering ribbon grain. It is available in ribbon stripe or mix grain. The recommended stains include those in the brown family.



White Oak has a Janka hardness rating of 1,360 lbf. It is from North America. The sapwood is a light pale color and the heartwood color is light to medium brown, usually golden or olive hues. It has a heavy texture that you can see and feel. The recommended stains are white/light colors, grays, browns, ebonized (black) and Muratti.



Black Walnut has a Janka hardness rating of 1,010 lbf. It is native to eastern and central North America. Steamed Black Walnut is treated with hot steam to darken its light sapwood and create a more uniform brown color. The color results in a warm chocolate brown. The wood has a buttery smooth texture. The recommended stains are in the brown family.



Unsteamed Black Walnut has a Janka hardness rating of 1,010 lbf. Our unsteamed walnut is locally and ethically sourced, mainly coming from trees removed from construction sites or downed trees from storms. It will have a variety of color with a distinct pale color sapwood and streaks of light to dark browns in the heartwood. Some slabs are lighter in color while others have a reddish hue. We do not regularly stain unsteamed Walnut.



Bubinga, otherwise known as **African Rosewood**, has a Janka hardness rating of 2,410 lbf. It is exceptionally hard and heavy in weight. It is found in the rainforests of West and Central Africa. It ranges from a vibrant pink-red to deeper red brown with purple to black streaks. It is known for its rosewood-like appearance despite not being a true rosewood. We do not usually recommend staining Bubinga.